


Evidence of Performance

Evidence of performance: Safety barrier glazing - Pendulum body impact resistance



Test report

No. 12-001323-PR02
(PB-H05-09-en-01)

Client	ALUMINCO S.A. Megali Rahi 32011 Inofita Viotias Greece
Product	Spandrel panel
Designation	- F50 HORIZON FRAME WITH 10 mm GLASS - CRYSTALLINE F85 TYPE A10 WITH 10mm GLASS
Performance-relevant product details	<u>F50 Horizon FRAME WITH 10 mm GLASS</u> Glass: 5 mm TSG / 4 x 0,38 mm PVB / 5 mm TSG Pane dimensions (W x H): 1,033 mm x 933 mm Glass fixing devices: F50-310/F50-3K10 and F50-203/F50-223 <u>CRYSTALLINE F85 TYPE A10 WITH 10mm GLASS</u> Glass: 5 mm TSG / 4 x 0,38 mm PVB / 5 mm TSG Pane dimensions (W x H): 960 mm x 958 mm Glass fixing devices: F85-904; F85-903 and F85-201
Support	Linear support at bottom and top
Special features	Glass: TSG Edge protection to be applied to the product
Result	Loadbearing capacity of safety barrier glazing  Categorie B: 700 mm drop height

Basis

Technische Regeln für die Verwendung von linienförmig gelagerten Verglasungen (Technical rules for safety barrier glazing with linear support) (TRAV)

Version: 2003-01

Prüfbericht 12-001323-PR02 (PB-H05-09-en-01) vom 05. Dezember 2012

Representation



Instructions for use

This test report is intended for submission to the supreme building control authorities to provide evidence of the suitability of safety barrier glazing for individual approval.

Validity

The data and detailed results given refer solely to the tested / described test specimen. The test /assessment does not allow any statement to be made on any further characteristics regarding performance and quality of the product.

Notes on publication

The ift Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

The cover sheet can be used as an abstract.

Contents

The report comprises a total of 13 pages

ift Rosenheim
01.02.2013

Karin Lieb, Dipl.-Ing. (FH)
Head of Testing Department
Building Material & Semifinished Products

Andreas Schmidt
Operating Testing Officer
Materials Testing